



YUAN TONG



CAN / H - SC
Calcined Diatomite Filter Aid

TYPICAL PHYSICAL PROPERTIES

Description	Calcined diatomite filter aid
Color	Pink
Specific Gravity (g/cm ³)	2.2
Moisture (% Maximum)	0.3
PH	7
Permeability (Darcy)	0.12
Wet Density (g/cm ³)	≤ 0.44
+ 150 μm (%)	≤ 5
Ignition Loss (%)	0.5

PARTICLE SIZE DISTRIBUTION (%)

>40 μ	16.3
40-20	34.3
20-10	24.4
10-5	14.0
5-2	8.2
<2	2.8
Median Particle Size μ	20.3

Chemical Analysis (%)

SiO ₂	92.1
Al ₂ O ₃	4.0
Fe ₂ O ₃	1.8
CaO	0.4
MgO	0.4
Na ₂ O	0.4
Others	0.9

Jilin Yuantong Mineral Co., Ltd.

Diatomaceous Earth Industrial Park, Linjiang City, Jilin province, China

<https://www.dadidiatomite.com>